


# SharkBite<sup>™</sup> PEX-a Blue PEX-a Tubing

SharkBite™ PEX-a is a cross-linked polyethylene tubing designed for use in residential and commercial applications.

### **Specification Data**



Tubing Dimensions							
Nominal Size (CTS)	O. D. (in)	Wall Thickness (in)	Approx. I.D. (in)	Weight per ft. (lb.)	Volume per ft. (gal.)		
1/2"	0.625 ± 0.004	0.070 + 0.010	0.475	0.053	0.009		
3/4"	0.875 ± 0.004	0.097 + 0.010	0.671	0.102	0.018		

Tolerances referenced from ASTM F876.

# Applications

Potable water distribution, radiant heating, direct burial, embedded in concrete, snow & ice melting, geothermal groundloops, turf conditioning, municipal water service lines, fire suppression & plenum application.

#### Materials

Cross-Linked Polythethylene / PEX-a / Peroxide Method

Materials Designation Code - PEX 5306				
(5) Chlorine Resistance	Rated to continuously recirculate hot water at 140°F (40°C)			
(3) UV Resistance	Six -month UV resistance			
	160 psi @ (33°F - 70°F) (0.5°C - 21°C)			
(06) Hydrostatic Stress	100 psi @ 180°F (80°C)			
	80 psi @ 200°F (93°C)			

## **Certifications & Listings**

ASTM F876, ASTM F877, NSF/ ANSI 14, NSF/ANSI/CAN 61, NSF/ ANSI/CAN 372, ASTM F2023, ASTM F2657, CSA B137.5, ASTM E84CAN/ULC S102.2, ASTM E119CAN/ULC S101, UL 1821-2003



US 18777004242 | sales@sharkbite.com | sharkbite.com Canada 18888200120 | canadasales@rwc.com

This information is proprietary to RWC and is subject to change without notice. It may not be reproduced in part or whole without written authorization.

Part number and description				
Part #	PEX Tubing (Coil)			
UA60B100	1/2" 100' Coil			
UA60B300	1/2" 300' Coil			
UA70B100	3/4" 100' Coil			
UA70B300	3/4" 300' Coil			
UA80B100	1" 100' Coil			

Part #	PEX Tubing (Straight Length)
UA60B10	1/2" 10' Straight Length
UA60B20	1/2" 20' Straight Length
UA70B10	3/4" 10' Straight Length
UA70B20	3/4" 20' Straight Length
UA80B20	1" 20' Straight Length

#### **Bend Radius**

Unsupported Bend Radius = 6 X O.D.

#### **Expansion & Contraction Rate**

Expansion rate: 1.1" / 10°F / 100'

For more technical data, visit the product at: https://www.sharkbite.com/products/potable-pex-a

Flodoct Sobilittat					
Name					
Date					
Architect/Owner					
Contractor					
Tag					
Notes					

Rev 1.1 / 07-18-23 EN-US

**Droduct Submittal** 

